

Component - Plastics

E150608

Guide Information

WAH HONG INDUSTRIAL CORP

11ST FL-6 235 CHUNG CHENG 4TH RD, KAOHSIUNG 801 TW

WH-8200

Unsaturated Polyester (UP), furnished as pellets

<u>Color</u>	<u>Min. Thk</u> <u>(mm)</u>	<u>Flame</u> <u>Class</u>	<u>HWI</u>	<u>HAI</u>	<u>RTI</u> <u>Elec</u>	<u>RTI</u> <u>Imp</u>	<u>RTI</u> <u>Str</u>
ALL	0.75	V-0	1	0	160	150	150
	3.0	V-0	0	0	180	160	160
Comparative Tracking Index (CTI): 0				Inclined Plane Tracking (IPT) kV: -			
Dielectric Strength (kV/mm): 36				Volume Resistivity (10 ^x ohm-cm): 14			
High-Voltage Arc Tracking Rate (HVTR): 0				High Volt, Low Current Arc Resis (D495): 4			
Dimensional Stability (%): -							

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

IEC and ISO Test Methods				
Test Name	Test Method	Units	Thk (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	0.75	V-0 (ALL)
			3.0	V-0 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	°C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	°C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	°C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	°C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-2	kJ/m ²	-	-